



Fabric Range

Kozane[®] Original
Kozane[®] Pro

Kozane[®] Extreme
Kozane[®] Pyro

Kozane[®] Invicta
Kozane[®] Supreme

Kozane® Original

Art. No. 500.2100

Initially designed as a lining for Granberg gloves, Kozane® Original offers maximum cut, tear and puncture resistance. This unique three-dimensional knitted fabric combines a high-performance top layer with a soft polyester bottom layer for optimum comfort and protection. Unlike other leading brands, Kozane® Original is suitable for use in direct contact with food.



Applications:






- ✓ Cut-resistant lining for gloves
- ✓ Anti-theft bags, covers, luggage, and upholstery
- ✓ Motorcycle apparel
- ✓ Cut resistant Footwear
- ✓ Slash resistant mattress covers for prisons and correction facilities

Sectors:

Glass and Metal fabrication, Car Manufacturing, Security, Sports and Leisure

EN 388: 2016 6.1 Abrasion	Level 3
EN 388: 2016 6.2 Blade cut resistance	Level X*
EN 388: 2016 6.4 Tear resistance	Level 4
EN 388: 2016 6.5 Puncture resistance	Level 4
EN 388: 2016 6.3 Cut resistance method (EN ISO 13997:1999)	Level F
ANSI ASTM F2992-15	Cut A5 (Cut Score: 2,512g)

**x stands for not tested. As per clause 6.2.6 of EN 388:2016 for materials dulling the blades, if after the first sequence the number of cycles Cn+1 is greater than 3 times Cn in one of the tested specimens, the EN ISO 13997:1999 Cut resistance method as per clause 6.3 shall be performed and this method becomes the reference test method for the assessment of the protection against cut risks.*

Weight	470g/m2
Roll width	1.77m
Roll length	18m
Colour	White (can be made available in black)
Safety and care instructions	    

Kozane® Pyro

Art. No. 500.2009

Originally designed as a lining for Granberg gloves, Kozane® Pyro's unique composition offers outstanding cut and heat resistance. This exceptional three-dimensional knitted fabric combines a high-performance top layer with a soft, FR bottom layer for optimum comfort and protection.



EN 388: 2016 6.1 Abrasion	Level 3
EN 388: 2016 6.2 Blade cut resistance	Level X*
EN 388: 2016 6.4 Tear resistance	Level 4
EN 388: 2016 6.5 Puncture resistance	Level 1
EN 388: 2016 6.3 Cut resistance method (EN ISO 13997:1999)	Level F
EN 407:2004 Clause 5.2 Contact Heat	Level 1 (100°C for ≥ 15 seconds)






**x stands for not tested. As per clause 6.2.6 of EN 388:2016 for materials dulling the blades, if after the first sequence the number of cycles Cn+1 is greater than 3 times Cn in one of the tested specimens, the EN ISO 13997:1999 Cut resistance method as per clause 6.3 shall be performed and this method becomes the reference test method for the assessment of the protection against cut risks.*

Applications:

- ✓ Cut and heat resistant lining for gloves
- ✓ PPE Manufacturing - Cut and heat resistant arm guards, aprons, chaps, clothing
- ✓ Cut and heat resistant protective clothing for Security/Army – can be personalised with camouflage print

Sectors:

Glass and Metal fabrication, Car Manufacturing, Security/Army

Weight	545g/m2
Roll width	1.90m
Roll length	18m
Colour	Green
Safety and care instructions	    

Kozane® Pro

Art. No. 500.3503

Konzane® Pro is the lightest of its class, offering high levels of cut, puncture and tear resistance, while being breathable and soft. Fully washable and designed primarily for garment manufacturing.



Applications:






- ✓ Cut and slash-resistant clothing
- ✓ Cut-resistant lining for gloves
- ✓ Anti-theft bags, luggage and upholstery
- ✓ Motorcycle, outdoor and extreme sports apparel (speed skating, hockey, speed boating, etc.)
- ✓ Cut resistant Footwear

Sectors:

Sports and Leisure, Glass and Metal fabrication, Car Manufacturing, Security

EN 388: 2016 6.1 Abrasion	Level 1
EN 388: 2016 6.2 Blade cut resistance	Level X*
EN 388: 2016 6.4 Tear resistance	Level 4
EN 388: 2016 6.5 Puncture resistance	Level 3
EN 388: 2016 6.3 Cut resistance method (EN ISO 13997:1999)	Level E
ANSI ASTM F2992-15	Cut A6 (Cut Score: 3,743g)

**x stands for not tested. As per clause 6.2.6 of EN 388:2016 for materials dulling the blades, if after the first sequence the number of cycles Cn+1 is greater than 3 times Cn in one of the tested specimens, the EN ISO 13997:1999 Cut resistance method as per clause 6.3 shall be performed and this method becomes the reference test method for the assessment of the protection against cut risks.*

Weight	345 g/m2
Roll width	1.98m
Roll length	18m
Colour	White, Other colours available, please email us for further enquiries
Safety and care instructions	    

Kozane® Invicta

Art. No. 500.2019

Konzane® INVICTA range features outstanding tear and abrasion resistance, with added cut and puncture resistance.



EN 388: 2016 6.1 Abrasion	Level 4
EN 388: 2016 6.2 Blade cut resistance	Level X*
EN 388: 2016 6.4 Tear resistance	Level 4
EN 388: 2016 6.5 Puncture resistance	Level 4
EN 388: 2016 6.3 Cut resistance method (EN ISO 13997:1999)	Level B

**x stands for not tested. As per clause 6.2.6 of EN 388:2016 for materials dulling the blades, if after the first sequence the number of cycles Cn+1 is greater than 3 times Cn in one of the tested specimen, the EN ISO 13997:1999 Cut resistance method as per clause 6.3 shall be performed and this method becomes the reference test method for the assessment of the protection against cut risks.*






PATENT PENDING

Applications:

- ✓ Tear-resistant clothing and bedding for mental health and prison/corrections
- ✓ Extremely durable footwear, luggage, upholstery
- ✓ Abrasion resistant protective motorcycle apparel
- ✓ Reinforcements (i.e. knees and elbows) for puncture, tear and abrasion resistance

Sectors:

Sports and Leisure, Healthcare, Prisons and Corrections, Security/Army

Weight	470 g/m2
Roll width	1.87m
Colour	Black and Grey
Safety and care instructions	    

Kozane® Extreme

Art. No. 500.3100

Konzane® Extreme offers the optimum combination between outstanding levels of protection and comfortability. While offering the highest cut, puncture and tear resistance. Kozane® Extreme is breathable and soft. Fully washable and designed primarily for garment manufacturing.



EN 388: 2016. 6.1 Abrasion	Level 3
EN 388: 2016. 6.2 Blade cut resistance	Level X*
EN 388: 2016. 6.4 Tear resistance	Level 4
EN 388: 2016. 6.5 Puncture resistance	Level 4
EN 388: 2016. 6.3 Cut resistance method (EN ISO 13997:1999)	Level F
ANSI ASTM F2992-15	Cut A8 (Cut Score: 5,215g)






**x stands for not tested. As per clause 6.2.6 of EN 388:2016 for materials dulling the blades, if after the first sequence the number of cycles Cn+1 is greater than 3 times Cn in one of the tested specimens, the EN ISO 13997:1999 Cut resistance method as per clause 6.3 shall be performed and this method becomes the reference test method for the assessment of the protection against cut risks.*

Applications:

- ✓ Cut and slash-resistant clothing
- ✓ Anti-theft bags, luggage and upholstery
- ✓ Motorcycle, outdoor and extreme sports apparel
- ✓ Cut resistant Footwear
- ✓ Bite and scratch resistant clothing for professionals in mental health and special education

Sectors:


Glass and Metal fabrication, Car Manufacturing, Security, Healthcare, Sports and Leisure, Mining, Recycling, Paper and Pulp

Weight / surface density	375 g/m2
Roll width	2.05m
Roll length	18m
Colour	Black
Safety and care instructions	    

Kozane® Supreme

Art. No. 500.1005

Konzane® Supreme reaches the highest possible cut resistance level according to the American standard ANSI ASTM F2992-15, an unprecedented ANSI A9 for a knitted fabric, previously only achieved by chain mail. While offering the highest cut, puncture, and tear resistance, Konzane® Supreme is soft and breathable, which makes it suitable for manufacturing cut resistant products across a variety of sectors.



Applications:

- ✓ Cut and slash-resistant clothing
- ✓ Anti-theft bags, luggage, and upholstery
- ✓ Motorcycle, outdoor and extreme sports apparel
- ✓ Cut resistant Footwear

Sectors:

Glass and Metal fabrication, Car Manufacturing, Security, Healthcare, Sports and Leisure, Mining, Recycling, Paper and Pulp

EN 388: 2016. 6.1 Abrasion	Level 4
EN 388: 2016. 6.2 Blade cut resistance	Level X*
EN 388: 2016. 6.4 Tear resistance	Level 4
EN 388: 2016. 6.5 Puncture resistance	Level 4
EN 388: 2016. 6.3 Cut resistance method (EN ISO 13997:1999)	Level F
ANSI ASTM F2992-15	Cut A9 (Cut Score: 7,005g)

**x stands for not tested. As per clause 6.2.6 of EN 388:2016 for materials dulling the blades, if after the first sequence the number of cycles Cn+1 is greater than 3 times Cn in one of the tested specimens, the EN ISO 13997:1999 Cut resistance method as per clause 6.3 shall be performed and this method becomes the reference test method for the assessment of the protection against cut risks.*

Weight	531 g/m2
Roll width	1.98m
Roll length	18m
Colour	Black
Safety and care instructions	